



Ultra-Drain Guard, Reusable Model[®]

High Flow Material Specifications

Physical Properties	Unit	Standard	Test Result
Grab Tensile	lbs	ASTM D 4632	295 x 230
Grab Elongation	%	ASTM D 4632	33 x 20
CBR Puncture	lbs	ASTM D 6241	800
Trapezoid Tear Strength	lbs	ASTM D 4533	130 x 110
UV Resistance 2500 hours	%	ASTM D 4355	70
AOS	US Sieve	ASTM D 4751	30
Flow Rate	GPM / ft ²	ASTM D 4491	360
Permittivity	s ⁻¹	ASTM D 4491	4.87
% Open Area (POA)	%	COE 22125-86	28

