



Ultra-Drain Guard, Reusable Model[®]

Regular Flow Material Specifications

Physical Properties	Unit	Standard	Test Result
Grab Tensile	lbs	ASTM D 4632	275 x 240
Breaking Strength	kN/m	ASTM D 4595	17 x 14
CBR Puncture	lbs	ASTM D 6241	940
Trapezoid Tear Strength	lbs	ASTM D 4533	75 x 80
UV Resistance 500 hours	%	ASTM D 4355	65
AOS	US Sieve	ASTM D 4751	35
Flow Rate	GPM / ft ²	ASTM D 4491	40
Permittivity	s ⁻¹	ASTM D 4491	0.45

