

# Chemical Compatibility Guide - Polyurethane

For: Ultra-Spill Berms, Ultra-Drain Seals, and Ultra-Drain Plugs

Chemical	Chemical Class	Swelling (0-2)	Visible Degradation (0-2)	Rating
Acetone	Ketones	2	0	NR
Acetonitrile	Nitriles	1	0	FAIR
Aluminum Salts	Aluminum Compounds	0	0	GOOD
Barium Salts	Barium Compounds	0	0	GOOD
Benzyl Alcohol	Hydroxyl Compounds	1	1	FAIR
Boric Acid	Inorganic Acids	0	0	GOOD
Butanol	Hydroxyl Compounds	0	0	GOOD
Calcium Chlorite	Calcium Compounds	0	0	GOOD
Carbon Disulfide	Sulfur Compounds	1	0	FAIR
Cupric Chloride	Copper Compounds	0	0	GOOD
Cyclohexanone	Ketones	1	2	NR
Dichloromethane	Halogen Compounds	2	2	NR
Diethylamine	Aliphatic Amines	1	1	FAIR
Dimethylformamide	Aliphatic Amides	2	2	NR
Ethyl Acetate	Carboxylic Esters	1	0	FAIR
Formaldehyde	Aliphatic Aldehydes	0	0	GOOD
Gasoline	Aromatic Hydrocarbons	0	0	GOOD
Gycol Ether	Ethers	0	0	GOOD
Hexane	Aliphatic Hydrocarbons	0	0	GOOD
Hydrochloric Acid (37%)	Inorganic Acids	0	2	NR
Hydrogen Peroxide (30%)	Peroxides	1	0	FAIR
Hydrofluoric Acid (48%)	Inorganic Acids	0	2	NR
Jet Fuel (JP-5)	Aliphatic Hydrocarbons	0	0	GOOD
Kerosene	Hydrocarbons	0	0	GOOD
Metahanol	Aliphatic Hydroxylic Compounds	0	0	GOOD
Methyl Ethyl	Ketone Aliphatic Ketones	2	0	NR
Mineral Oil	Aliphatic and Alicyclic Hydrocarbons	0	0	GOOD
Naphtha	Hydrocarbons	0	0	GOOD
Nitrobenzene	Nitro Compounds	0	2	NR
Phenol	Aromatic Hydroxylic Compounds	0	2	NR
Propylene Glycol	Hydroxylic Compounds	0	0	GOOD
Sodium Hydroxide (50%)	Inorganic Bases	0	0	GOOD
Sulfuric Acid (98%)	Inorganic Acids	0	2	NR
Sulfuric Acid (50%)	Inorganic Acids	0	2	NR
Tetrachloroethylene	Halogen Compounds (Vinyl Halides)	0	0	GOOD
Tetrahydrofuran	Alicyclic Ethers	2	2	NR
Toluene	Aromatic Hydrocarbons	1	0	FAIR
1,1,1-Trichloroethane	Aliphatic Halogen Compounds	1	0	FAIR
Trichloroethylene	Halogen Compounds (Vinyl Halides)	1	0	FAIR
Triethylamine	Aliphatic Amines	0	0	GOOD
Turpentine	Hydrocarbons	0	0	GOOD
Water	Misc.	0	0	GOOD

## KEY:

### Swelling:

Visually rated from 0-2;  
0 = none  
1 = slight  
2 = significant

### Degradation:

Visually rated from 0-2;  
0 = none  
1 = slight  
2 = significant

### Ratings:

NR (Not Recommended):  
Significant degradation  
or swelling  
FAIR: Slight swelling  
GOOD: No swelling

## \*Important User Notice For Both The Polyurethane and Polyethylene Chemical Compatibility Guides

The data contained herein is a compilation of existing published data from leading manufacturers of polyethylene and polyurethane and does not represent actual testing performed by UltraTech International, Inc.

This listing is offered only as a guide and utilizes information which, to the best of UltraTech's knowledge, is accurate and reliable. Due to variables and conditions of application beyond the control of UltraTech, none of the data shown in this guide is to be construed as a guarantee, expressed or implied. UltraTech International, Inc. assumes no responsibility, obligation or liability in conjunction with the use or misuse of the information herein.